


SAM™ Data Sheet SAM-1064-12-16ps-x, $\lambda = 1064 \text{ nm}$

Laser wavelength	$\lambda = 1064 \text{ nm}$
High reflection band (R > 88%)	$\lambda = 1050 \dots 1120 \text{ nm}$
Absorbance	$A_0 = 12 \%$
Modulation depth	$\Delta R = 6 \%$
Non-saturable loss	$A_{ns} = 6 \%$
Saturation fluence	$\Phi_{sat} = 32 \mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 16 \text{ ps}$
Damage threshold	$600 \text{ MW}/\text{cm}^2$
Chip area	4mm x 4mm; other dimensions on request
Chip thickness	400 μm ; optional: 150 μm on request
Protection	the SAM is protected with a dielectric front layer

Mounting option **x** denotes the type of mounting as follows:


x = 0	unmounted
x = 12.7 g	glued on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 g	glued on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = 12.7 s	soldered on a gold plated Cu-cylinder with 12.7 mm \varnothing
x = 25.4 s	soldered on a gold plated Cu-cylinder with 25.4 mm \varnothing
x = 25.0 w	soldered on a water cooled Cu-cylinder with 25.0 mm \varnothing
x = FC	mounted on a 1 m monomode fiber cable with FC connector

Low intensity spectral reflectance



SAM 375 IIb

Saturation measurement



Pump-probe measurement

