SA – Saturable Absorber

Product Overview

BATOP GmbH
Stockholmer Str. 14
07747 Jena
Germany
Phone: +49 3641 634009 - 0
URL: http://www.batop.de
e-mail: info@batop.de

- Saturable absorber for use in transmission applications
- For passive mode-locking of solid state, ring or fiber ring lasers



SA 1020/1030	Laser wavelength	λ = 980 nm – 1040 nm
	Absorptance	A_0 = 34 - 40 %
	Relaxation time	τ ~ 500 fs / 3 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2
SA 1064	Laser wavelength	λ = 1030 nm – 1090 nm
	Absorptance	A_0 = 14 – 40 %
	Relaxation time	τ ~ 500 fs – 37 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2
SA 1340	Laser wavelength	λ = 1300 nm – 1460 nm
	Absorptance	A_0 = 22 %
	Relaxation time	τ ~ 20 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2
SA 1550	Laser wavelength	λ = 1400 nm – 1600 nm
	Absorptance	A_0 = 6 – 58 %
	Relaxation time	τ ~ 2 – 20 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2
SA 2000	Laser wavelength	λ = 1900 nm – 2100 nm
	Absorptance	A_0 = 1 - 43 %
	Relaxation time	τ ~ 10 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2
SA 2800	Laser wavelength	λ = 2500 nm – 3000 nm
	Absorptance	A_0 = 10 %
	Relaxation time	τ ~ 10 ps
	Saturation fluence	Φ_{sat} = 300 µJ/cm^2

For other wavelengths and parameters please ask!

Mounting Options



12.7 mm ∅ - Cu-Mount with ∅ 4 mm hole

25.0 mm ∅ - Cu-Mount with ∅ 4 mm hole

Backside of 25.0 mm ∅ - Cu-Mount with ∅ 4 mm hole

Fiber coupled SA

Chip area:	5 mm x 5 mm
Chip thickness:	625 µm semi – insulating GaAs, other thickness on request
Front side protection:	AR coating
Back side:	Polished and AR coated

Mounting:	▪ Unmounted
	▪ Glued on:
	  ▪ 12.7 mm ∅ Cu-mount with ∅ 4 mm hole
	  ▪ 25.0 mm ∅ Cu-mount with ∅ 4 mm hole
	▪ Fiber coupled (SMF, PMF)
	▪ Mounting on custom mounts on request

Spectral transmission / absorption:

SA 1020-40-500fs-X



SA 1064-40-500fs-X



SA 1550-25-2ps-X



SA 2000-25-10ps-X



Notes: